NC/QC/YPD/2020-21/SB/W5-1-CB12

Date: 09-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength)
(Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.)

Ref.: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	01-12-20	08-12-20	08	22500	360	16.00	16.07
	002	"	"	"	"	355	15.78	
	003	"	"	"	"	370	16.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB13

Date: 09-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}

Ref.: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	02-12-20	09-12-20	08	22500	365	16.22	**16.15**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	355	15.78	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB14 Date: 09-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	02-12-20	09-12-20	08	22500	375	16.67	**16.74**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	370	16.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB15 **Date: 09-12-2020**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	02-12-20	09-12-20	08	22500	380	16.89	**16.89**
	002	‘’	“	‘’	“	370	16.44	
	003	‘’	“	‘’	“	390	17.33	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB16

Date: 10-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-12-20	10-12-20	08	22500	385	17.11	**16.59**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	365	16.22	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB17 Date: 10-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-12-20	10-12-20	08	22500	370	16.44	**16.22**
	002	"	"	"	"	365	16.22	
	003	"	"	"	"	360	16.00	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB18

Date: 10-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07 days Compressive Strength)
[Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.]

Ref.: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-12-20	10-12-20	08	22500	365	16.22	16.30
	002	"	"	"	"	360	16.00	
	003	"	"	"	"	375	16.67	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

Date: 11-12-2020

NC/QC/YPD/2020-21/SB/W5-1-CB19

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	04-12-20	11-12-20	08	22500	380	16.89	**16.81**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	385	17.11	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/VPD/2020-21/SB/W5-1-CB20 Date: 11-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg Value
1	001	04-12-20	11-12-20	08	22500	360	16.00	16.07
	002	"	"	"	"	355	15.78	
	003	"	"	"	"	370	16.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB21 Date: 11-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	04-12-20	11-12-20	08	22500	365	16.22	**16.15**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	355	15.78	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB22

Date: 14-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	07-12-20	14-12-20	08	22500	375	16.67	**16.74**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	370	16.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT ★ Bangalore ★

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB23 Date: 14-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	07-12-20	14-12-20	08	22500	380	16.89	**16.89**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	390	17.33	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT

Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB24

Date: 14-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}

Ref.: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	07-12-20	14-12-20	08	22500	385	17.11	**16.59**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	365	16.22	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Dwarakanagara.

NEWZEN CONSULTANT

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB1A

Date: 25-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	27-11-20	25-12-20	28	22500	505	22.44	**22.81**
	002	"	"	"	"	520	23.11	
	003	"	"	"	"	515	22.89	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB2A

Date: 25-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg Value
1	001	27-11-20	25-12-20	28	22500	515	22.89	22.59
	002	"	"	"	"	500	22.22	
	003	"	"	"	"	510	22.67	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB3A

Date: 25-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength)
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	27-11-20	25-12-20	28	22500	515	22.89	**22.52**
	002	"	"	"	"	495	22.00	
	003	"	"	"	"	510	22.67	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT * Bangalore *

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB4A Date: 26-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	28-11-20	26-12-20	28	22500	510	22.67	**22.37**
	002	"	"	"	"	495	22.00	
	003	"	"	"	"	505	22.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT • Bangalore •

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB5A Date: 26-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	28-11-20	26-12-20	28	22500	525	23.33	**22.96**
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	510	22.67	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB6A

Date: 26-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	28-11-20	26-12-20	28	22500	520	23.11	**22.74**
	002	"	"	"	"	510	22.67	
	003	"	"	"	"	505	22.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/YPD/2020-21/SB/W5-1-CB7A

Date: 28-12-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to Roads and Drains in Vinayakanagara, Kattigenahalli and Dwarakanagara Surrounding area in Ward No: 05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s SLP Infra Engineers Pvt Ltd (H S Yashwanth Gowda), Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	30-11-20	28-12-20	28	22500	500	22.22	**22.44**
	002	"	"	"	"	510	22.67	
	003	"	"	"	"	505	22.44	

The result of the materials tested meets the standards and hence can be used for the work.
Sample Collected Site : Vinayakanagara.

NEWZEN CONSULTANT

Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner